

# Degafloor CP TD

Designed specifically for top decks of multi-storey car parks, Degafloor CP TD offers outstanding flexibility to create a highly durable, waterproof finish.

Manufactured from technically advanced methyl methacrylate resin, this cold applied system offers outstanding durability, flexibility and resistance to extreme operating conditions.

Suitable for both asphalt and concrete substrates.

## Features and benefits

### ■ Much faster to install than traditional car park finishes

*Cures fully within just 1 hour of installation*

### ■ Cold applied

*None of health and safety issues associated with hot trades, no big vehicles, minimised environmental impact*

### ■ Excellent UV resistance

*Provides crack free performance and colour stability*

### ■ Flexible warranty options available

### ■ Wide range of vibrant colours

### ■ Incredibly strong bond to concrete and asphalt substrates

### ■ Excellent skid resistance

*That can be tailored to deliver specific PSV requirements*

### ■ Excellent chemical and road salt resistance

### ■ Superb thermal stability

*No softening / degradation during summer months, flexible in winter months*

## Fields of application include:

- Car park top decks
- Other exposed parking decks requiring waterproofing
- Basement car parks
- Footbridges



# Degafloor CP TD

## Substrate preparation

All substrates must be clean, dry and free from contamination. Concrete substrates must be capable of accepting a resin finish and this is best achieved by mechanical means (shotblasting, planing or diamond grinding).

Concrete substrates must be primed using Degafloor 112 primer applied at approx. 0.4kg/m<sup>2</sup>.

Asphalt substrates do not require separate priming.

## Cure times

Degafloor CP TD cures fully within just 1 hour of installation (both chemically and physically). The cure time remains unaffected at temperatures down to 0°C.

## Chemical resistance

Excellent resistance to diesel, engine oils and road salts. Limited resistance to unleaded and super unleaded petrol.

Traffic Yellow (RAL1023)  
Traffic Red (RAL3020)  
White  
Traffic Green (RAL6024)  
Black  
Traffic Grey (RAL7043)  
Mid Grey (RAL7045)  
Traffic Purple (RAL4006)  
Traffic Blue (RAL5017)



## Available pack sizes

25kg, 200kg, 900kg

## Health and Safety

All resins are manufactured to ISO 9001:2008, ISO 14001:2004 and BS OHSAS 18001:2007 standards and comply with all current EU hygiene of foodstuffs regulation.

All resins are non-toxic and certified to confirm physiological inoffensiveness.

## Disclaimer

Degafloor Ltd endeavour to ensure that all information and advice given is accurate and correct. However, the company cannot take responsibility for the selection of products for specific applications. Therefore any prospective customers should satisfy themselves that the product is suitable for the environment in which it will be installed. Accordingly, Degafloor cannot take responsibility for the selection, by others, of a product unsuitable for the application. The information detailed in this leaflet is liable to change without prior notification.

Degafloor Ltd, Crusader House, High Street,  
Maxey, Peterborough UK PE6 9HQ

T: +44 (0)1778 342 545 F: +44 (0)1778 380 912  
E: [marketing@degafter.com](mailto:marketing@degafter.com) W: [www.degafter.com](http://www.degafter.com)